

presto Thermo Paint

Technical Information



High-heat-resistant, black special lacquer with excellent adhesion. To varnish objects which are exposed to high heat. Also suitable for use in a spray gun. Ideal for the painting of exhaust pipes on bikes and cars, engine blocks, but also for oven pipes, BBQ casings and much more.

Ord.-no: 287664

Quality & properties

- Fast drying
- Highly heat resistant up to 800 ° C
- Very good coverage
- Good weather resistance
- Scratch-proof

Physical & chemical data

- Base: Special resin
- Colourname: black
- Degree of gloss: mat GU
- Efficiency: 250 ML – 2-3 m²
- Dry to touch: 60 min
- Dust dry: 30 min
- Completely dry: 1 h
- Surfaces: metal
- Minimum Working Temperature: 10 °C
- Maximum Working Temperature: 30 °C
- Storage stability: 5 y
- Content: 250 ML

How to use

Remove rust, oil and grease from the surface to be painted.
Then thoroughly sand resp. sandblast; the surface has to be blank to the bare metal!
The ground has to be dry and free from dust and fat.
No primer necessary. The best results will be achieved on bare metal!
Stir up vigorously before use.
Apply with a fine artist's brush 1-2 thin coats. Let dry. Important: the thinner the paint coat, the better the temperature-resistance and the adhesion will be.
Stoving for approx. 30 minutes at 160 - 200°C is condition for curing and thus for the full resilience of the paint coat (heat-resistance and fuel-resistance!).
Do not use on chrome-plated parts!
Use only in well ventilated areas.

Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

As of May 7, 2025 – This release replaces all eventually earlier issued versions.