

presto Epoxy putty

Technical Information



2-component, solvent-free epoxy fine putty for the use above water and especially underwater environment on all customary boatbuilding materials. The putty levels out slight unevennesses and fills capillary cracks. It is extremely water-resistant and scarcely shrinks. Especially recommended for the repair of osmosis damages.

Ord.-no: 600555

Quality & properties

- Extremely water-resistant
- Solvent- and phenole-free, therefore low unpleasant odour
- Nearly no shrinkage during curing
- Easy processing
- Good adhesion
- Very easy to sand
- Resistant to diluted acids, diluted lyes, inorganic salt solutions, benzene and petrol, fats and oils

Physical & chemical data

- Base: Base10
- Colourname: white-grey
- Minimum Working Temperature: 12 °C
- Maximum Working Temperature: 30 °C
- Flash point: unbekannt
- Storage stability: 2 y
- Content: 500 G

How to use

The area to be repaired should be derusted, clean, dry, free of grease and sanded.
 No primer necessary.
 Putty (A-Component) and hardener (B-Component) have to be dosed exactly and mixed thoroughly.
 The mixing ratio putty : hardener is 2 : 1 by weight.
 The putty can be applied up to a height of 2 cm per workstep without shrinking.
 The open working time is 1 hour at +20° C.
 Within 24 hours the repair area can be sanded.
 To optimize the adhesion, we recommend to sand the previous layer slightly before the next workstep.
 Do not return remains of mixed material into the can!

Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

As of May 7, 2025 – This release replaces all eventually earlier issued versions.