

## presto Plastic Primer

## Technical Information



presto Plastic Primer is a bonding agent for the final varnishing of car plastic parts with presto or DUPLI-COLOR spray paints.

Suitable for car parts, garden furniture and other objects of coatable hard plastics.

Applicable for following hard plastics: polyurethane (PUR), polystyrene (PS), polyamide (PA), polypropylene rubber, modified (EPDM), acrylic butadiene styrene plastics (ABS), glass-fibre reinforced plastics (GfK), hard polyvinyl chloride (Hard-PVC)

**Ord.-no:** 308066

### Quality & properties

- Applicable to almost all plastics
- Ideal base for the further paint build-up
- Fast drying
- Solvent-based product with special adhesion-promoting additives
- Good flow, smooth surface
- Suitable for indoors and outdoors applications
- Good resistance to outside influences

### Physical & chemical data

- Base: Special resin
- Colourname: transparent
- Efficiency: 400 ML – 5-6 m<sup>2</sup>
- Completely dry: 15 min
- Overcoatable: 15 min
- Minimum Working Temperature: 10 °C
- Maximum Working Temperature: 30 °C
- Flash point: n.a.
- Storage stability: 10 y
- Content: 400 ML

### How to use

- The surface has to be clean, dry and free from fat.
- If necessary, sand with grain 600 sandpaper. Remove abrasive dust.
- Shake can for 3 minutes before use.
- Test spray at an invisible spot.
- Apply max. 2 thin layers.
- Spray distance approx. 25 cm.
- After drying (approx. 15 minutes) coatable with acrylic, synthetic or nitro-combi lacquers.

### Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

### Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

### Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

**As of May 7, 2025** – This release replaces all eventually earlier issued versions.