

presto Zinc-Spray

Technical Information



Cold galvanization against corrosion. Excellent rust-protection for all iron metals, such as car bodies, exhaust systems, gates, machines, metal housings, metal fittings, fences etc. Especially suitable for the protection of welding seams and metals which are exposed to corrosion. For the colour-matching repair of zinc-plated surfaces, use presto Zinc-Alu-Spray.

Ord.-no: 165034, 308035

Quality & properties

Cathodic corrosion protection for all blank metals
For repairs according to DIN EN ISO 1461 Edition: 1999-03 (formerly DIN 50976)
Resistant to highest demands against corrosion
High-heat-resistant up to 600 °C
Particularly suitable for welding seams
High-grade zinc coating with more than 90 % zinc share in the dry film
Ideal for all metals in outside places, which are liable to rust

Physical & chemical data

Base: Special resin
Colourname: grey
Degree of gloss: mat GU
Efficiency:

- 150 ML – 0.4 m²
- 400 ML – 1-1.5 m²

 Dry to touch: 20 min
 Completely dry: 24 h
 Minimum Working Temperature: 10 °C
 Maximum Working Temperature: 30 °C
 Flash point: n.a.
 Storage stability: 10 y
 Content:

- 150 ML
- 400 ML

How to use

The surface must be clean, dry, rust and grease free.
 Due to the high density, the Zinc Spray has to be shaken for at least 2 minutes after you hear the noise of the mixing-balls. Otherwise the valve could block.
 Test spray at an invisible spot.
 Apply several covering coats.
 Do apply just thin coats to objects, which are exposed to high heat. If necessary, re-coat with temperature-resistant lacquer (test painting).
 Spray distance approx. 25 - 30 cm.
 It is not recommended to overpaint with other laquers.
 After drying (approx. 24 hours) primer and top coat can be applied.

Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

As of May 7, 2025 – This release replaces all eventually earlier issued versions.