



prestolith pro Universal putty is a 2-component polyester putty for professional use in garages, workshops, in machine-construction enterprises, metal-working, wood-processing and concrete-processing works, carpenter's shops. Especially suitable for the use in the presto dosing dispenser.

Fields of application:
- metal, wood, concrete

Ord.-no: 854958

Quality & properties

- Easy processing
- Good adherence
- Easy to sand, even after a longer period
- No more differentiation of surfaces like zinc-plated, hot dip galvanized or aluminium
- Resistant to weak acids and bases, propellants, solvents, water and de-icing salt
- High elasticity

Physical & chemical data

- Base: Polyester resin
- Colourname: ochre
- Completely dry: 20 min
- Overcoatable: 20 min
- Surfaces: metal, various plastics, wood, concrete
- Minimum Working Temperature: 12 °C
- Maximum Working Temperature: 30 °C
- Flash point: 31 °C
- Storage stability: 1.5 y
- Content: 3,00 KG

How to use

The area to be repaired should be derusted, clean, dry, free of grease and sanded.
Take the required amount of material from the can and mix it well with the corresponding quantity of hardener.
Apply the mixed material in the desired layer thickness.
After approx. 20 minutes the repaired spot can be sanded and painted.
Clean tools immediately after use, if necessary with a nitro thinner.
Do not return mixed material into the can.

Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

As of May 7, 2025 – This release replaces all eventually earlier issued versions.